PIPING SYSTEMS FOR WATER & WASTEWATER TREATMENT APPLICATIONS





WATER & WASTEWATER TREATMENT SOLUTIONS

- Process Piping
- Double Containment Pipng
- Ventilation Ductwork
- Valves, Automation and Instrumentation
- Electrical Systems

We build tough products for tough environments®



# IPEX Integrated Solutions for Water & Wastewater Treatment Plants

As one of the world's leading suppliers of industrial piping products; IPEX offers a comprehensive range of integrated solutions to meet the needs of water and wastewater facilities.

Superior to the competition, the IPEX system consisting of Pipe, Valves, and Fittings (PVF) ensures uniform performance throughout treatment facilities.



- Noncorroding properties ensure long-term performance coupled with low maintenance costs
- Lightweight thermoplastics are cost effective and easy to install
- Ease of installation and repair of systems makes IPEX the supplier of choice amongst facilities maintenance personnel
- IPEX products are available through an extensive network of local distributors
- Local sales representation provides support where and when you need it

- Onsite training, prior to installation, ensures systems are installed without issue
- Responsive product support is provided by our team of applications engineers, material scientists, technical sales representatives, and chemists
- Tool rentals are available should you need to service or expand an existing system
- Ask your sales representative for case histories showing similar installations



#### CORROSIVE & HIGH HUMIDITY VENTILATION DUCTWORK

IPEX's PVC and CPVC Ventilation ductwork are ideally suited for both high humidity and corrosive applications in Water and Wastewater Treatment Plants. These ducts can be used as a cost effective alternative to Stainless Steel.

Some typical applications include:

- Headwork building ventilation
- Flocculation and sedimentation ventilation
- Laboratory exhaust

#### **EMERGENCY FUEL SUPPLY**

# CustomGu@rd® Centra-Gu@rd®

CustomGuard<sup>®</sup> double containment piping systems are the ideal solution for the conveyance of petroleum products. Our systems satisfy the federal requirement 40 CFR 280 for underground storage tanks (UST)\*. This regulation requires all UST and the associated underground piping to be double contained. Installing

a double containment system will help to minimize down-time, mitigate risks, eliminate potential EPA issues, and reduce replacement and maintenance costs.



\* Please check with your local regional authority for specific requirements



## **AERATION & CO2 INJECTION**

#### Xirtec PVC Xirtec CPVC Duraplur

Throughout North America, our highly engineered products are widely used within the aeration and CO₂ injection process. Suitable products include Xirtec® PVC, Xirtec® CPVC (warmer climate), and Duraplus<sup>™</sup> Industrial ABS (colder climates).

- Xirtec PVC & Xirtec CPVC offer an economical alternative to traditional materials used in the aeration and CO<sub>2</sub> injection piping process.
- Duraplus<sup>™</sup> Industrial ABS offers additional impact strength and ductility even in cold weather environments.

### VALVES, ACTUATORS & INSTRUMENTATION

IPEX offers one of the most comprehensive ranges of high quality, high performance thermoplastic valves, actuators and instrumentation available today. Whether you require a valve for isolation, an actuator for control, or instrumentation to measure, IPEX has a solution to meet your needs.



Regulating

- Valve types include ball, butterfly, diaphragm, check, and specialty.
- Actuator types include pneumatic and electric for use in indoor and outdoor applications.
- Instrumentation includes monitors for Flow, Batch, Conductivity and PH.
- Material options such as PVC, CPVC, PP, PVDF, and ABS make our corrosion-resistant valves ideal for use in a wide variety of WTP and WWTP applications.

On/Off

Vented

### WATER, SLUDGE & CHEMICAL DISTRIBUTION

### Xirtec PVC Xirtec CPVC Duraplur enpure

Our superior plastic piping systems offer resistance to a broad spectrum of chemicals. Our products have been successfully used to transport:

- Coagulants, flocculants and precipitants
- pH control
- Disinfectants and oxidants
- Water (raw, potable, RO, DI)
- Sludge

# **CHEMICAL DISTRIBUTION ADDED PROTECTION**

# Guardian" CustomGuard<sup>®</sup> Centra-Guard<sup>®</sup>

Double Containment piping has an inner and an outer barrier with an interstitial space that is monitored for leaks. Almost all of the chemicals used in treatment plants are classified by the EPA as hazardous and should be double contained.





#### TREATED EFFLUENT DISCHARGE

#### Xirtec<sup>®</sup> **PVC IPEX CENTURION**<sup>®</sup>

IPEX PVC (up to 60" diameter) is the ideal solution for transporting treated water from the WWTP to the appropriate discharge point.



### **ELECTRICAL & AUTOMATION SYSTEMS**

Scepter Scepter JBox Sceptalight

Electrical and automation systems are subjected to harsh corrosive and humid environments. IPEX offers a wide range of lighting, conduit, fittings and junction boxes made from industrial grade PVC.



# **Common Chemicals in Water & Wastewater Treatment Plants**

Temperature are in Fahrenheit Swelling / Weight loss / Elongation at break

< 3% / < 0.5% / No Change

R<sup>MAX RATED TEMP</sup> – Resistant C – Limited Resistance < 8% / < 5% / decreased by < 50%

N – Not Resistant > 8% / > 5% / decreased by > 50%

A – Case by Case

		-	<b>A 1 1</b>	DVO		4.50		EDDM	EDNA	DTEE
	Chemical	Formula	Concentration	PVC	CPVC	ABS	PP-n	EPDM	FPM'	PIFE
Coagulants, Flocculants & Precipitants	Aluminum Sulfate (Alum)	Al2(SO4)·18H2O	Saturated	R <sup>140</sup>	R <sup>140</sup>	R <sup>160</sup>	R <sup>104</sup>	R <sup>140</sup>	R <sup>140</sup>	R <sup>248</sup>
	Aluminum Chloride	AICI3	Saturated	R <sup>140</sup>	R <sup>140</sup>	R <sup>160</sup>	R <sup>104</sup>	R <sup>140</sup>	R <sup>176</sup>	R <sup>248</sup>
	Calcium hydroxide (Lime)	Ca(OH) <sub>2</sub>	Aqueous	R <sup>140</sup>	R <sup>104</sup>	R <sup>68</sup>	R <sup>104</sup>	R <sup>176</sup>	R <sup>176</sup>	R <sup>248</sup>
	Ferric Chloride	FeCl <sub>3</sub>	Saturated	R <sup>140</sup>	R <sup>176</sup>	R <sup>104</sup>	R <sup>104</sup>	R <sup>176</sup>	R <sup>176</sup>	R <sup>248</sup>
	Ferric Sulfate	Fe <sub>2</sub> (SO <sub>4</sub> ) <sub>3</sub>	Saturated	R <sup>140</sup>	R <sup>140</sup>	R <sup>68</sup>	R <sup>104</sup>	R <sup>104</sup>	R <sup>176</sup>	R <sup>248</sup>
	Ferrous Sulfate (Copperas)	FeSO4·7H2O	Saturated	R <sup>140</sup>	R <sup>140</sup>	R <sup>140</sup>	R <sup>104</sup>	R <sup>176</sup>	R <sup>176</sup>	R <sup>248</sup>
	Polymer (PVC is typically used in	this application)		А	А	А	А	А	А	А
	Sodium Aluminate	Na2Al2O4	Saturated	R <sup>140</sup>	R <sup>200</sup>	R <sup>180</sup>	R <sup>70</sup>	R <sup>140</sup>	R <sup>140</sup>	R <sup>350</sup>
pH Control	Calcium Carbonate	CaCO <sub>3</sub>	Aqueous	R <sup>140</sup>	R <sup>176</sup>	R <sup>104</sup>	R <sup>104</sup>	R <sup>104</sup>	R <sup>104</sup>	R <sup>248</sup>
	Calcium Oxide	CaO	Saturated	R <sup>140</sup>	R <sup>176</sup>	R <sup>140</sup>	R <sup>104</sup>	R <sup>176</sup>	R <sup>176</sup>	R <sup>350</sup>
	Carbon Dioxide	CO <sub>2</sub>	100%	R <sup>140</sup>	R <sup>200</sup>	R <sup>140</sup>	R <sup>104</sup>	R <sup>176</sup>	R <sup>176</sup>	R <sup>248</sup>
	Magnesium Hydroxide	Mg(OH) <sub>2</sub>	Saturated	R <sup>140</sup>	R <sup>104</sup>	R <sup>140</sup>	R <sup>104</sup>	R <sup>176</sup>	R <sup>212</sup>	R <sup>248</sup>
	Magnesium Oxide	MgO	Saturated	R <sup>140</sup>	R <sup>200</sup>	R <sup>160</sup>	R <sup>104</sup>	R <sup>70</sup>	R <sup>70</sup>	R <sup>70</sup>
	Sodium Bicarbonate	NaHCO3	Saturated	R <sup>140</sup>	R <sup>140</sup>	R <sup>140</sup>	R <sup>104</sup>	R <sup>176</sup>	R <sup>212</sup>	R <sup>248</sup>
	Sodium Carbonate (Soda Ash)	NaCO3	Aqueous	R <sup>140</sup>	R <sup>176</sup>	R <sup>140</sup>	R <sup>104</sup>	R <sup>176</sup>	R <sup>176</sup>	R <sup>248</sup>
	Sodium Hydroxide (Caustic Soda)	NaOH	<50%	R <sup>104</sup>	А	Ν	R <sup>104</sup>	R <sup>140</sup>	Ν	R <sup>248</sup>
			>50%	R <sup>104</sup>	A	Ν	C <sup>104</sup>	R <sup>140</sup>	Ν	R <sup>248</sup>
	Carbonic Acid	H <sub>2</sub> CO <sub>3</sub>	Saturated	R <sup>104</sup>	R <sup>176</sup>	R <sup>104</sup>	R <sup>104</sup>	R <sup>176</sup>	R <sup>176</sup>	R <sup>248</sup>
	Hydrochloric Acid	HCI	<25%	R <sup>140</sup>	R <sup>176</sup>	R <sup>68</sup>	R <sup>104</sup>	R <sup>68</sup>	R <sup>176</sup>	R <sup>248</sup>
			<30%	R <sup>140</sup>	R <sup>176</sup>	Ν	R <sup>104</sup>	Ν	R <sup>140</sup>	R <sup>248</sup>
			<37%	R <sup>140</sup>	R <sup>140</sup>	Ν	R <sup>104</sup>	Ν	R <sup>104</sup>	R <sup>248</sup>
			>37%	R <sup>104</sup>	R <sup>68</sup>	Ν	Ν	Ν	R <sup>68</sup>	R <sup>248</sup>
	Sulfuric Acid	H <sub>2</sub> SO <sub>4</sub>	<50%	R <sup>140</sup>	R <sup>176</sup>	R <sup>68</sup>	C <sup>104</sup>	C <sup>68</sup>	R <sup>212</sup>	R <sup>248</sup>
	*Double Containment piping		<70%	C <sup>140</sup>	R <sup>176</sup>	Ν	C <sup>104</sup>	Ν	R <sup>176</sup>	R <sup>212</sup>
	Is recommended when the fluid temperature exceeds the		<78%*	C <sup>104</sup>	R <sup>104</sup>	Ν	C <sup>104</sup>	Ν	R <sup>176</sup>	R <sup>212</sup>
	maximum rated temperature.		<93%*	C <sup>104</sup>	R <sup>104</sup>	Ν	Ν	Ν	R <sup>176</sup>	R <sup>212</sup>
			<96%*	C <sup>104</sup>	R <sup>104</sup>	Ν	Ν	Ν	C <sup>140</sup>	R <sup>212</sup>
			96% - 98%*',**	C <sup>68</sup>	R <sup>104</sup>	Ν	Ν	Ν	Ν	R <sup>176</sup>
	Sodium Hexametaphosphate	[NaPO3]6	Saturated	R <sup>140</sup>	R <sup>180</sup>	-	R <sup>104</sup>	R <sup>180</sup>	R <sup>122</sup>	R <sup>122</sup>
Disinfectants, Odor Control & Color Removal	Aqua Ammonia <sup>††</sup>	NH <sub>3</sub>	Saturated	R <sup>140</sup>	Ν	Ν	R <sup>104</sup>	R <sup>140</sup>	Ν	R <sup>248</sup>
	Liquid Ammonium Sulfate (LAS)	(NH4)2SO4	Saturated	R <sup>140</sup>	R <sup>200</sup>	R <sup>140</sup>	R <sup>176</sup>	R <sup>176</sup>	R <sup>176</sup>	R <sup>248</sup>
	Calcium Hypochlorite	CA(OCI) <sub>2</sub>	Saturated	C <sup>104</sup>	R <sup>104</sup>	R <sup>70</sup>	R <sup>104</sup>	R <sup>104</sup>	R <sup>122</sup>	R <sup>212</sup>
	Chlorine dioxide	CIO <sub>2</sub>	14 g/L	R <sup>104</sup>	R <sup>68</sup>	-	Ν	Ν	C <sup>68</sup>	R <sup>248</sup>
	Hypochlorous Acid	HCIO	10%	R <sup>140</sup>	C <sup>176</sup>	-	R <sup>68</sup>	R <sup>68</sup>	R <sup>140</sup>	R <sup>248</sup>
	Hydrogen Peroxide <sup>tt</sup>	H <sub>2</sub> O <sub>2</sub>	<5%	R <sup>140</sup>	R <sup>104</sup>	-	C <sup>68</sup>	R <sup>68</sup>	R <sup>140</sup>	R <sup>248</sup>
			>5%	R <sup>104</sup>	C <sup>68</sup>	-	-	-	R <sup>68</sup>	R <sup>248</sup>
	Ozone (Aqueous)	O3	0.5mg/L in H <sub>2</sub> O	R <sup>68</sup>	R <sup>68</sup>	Ν	Ν	R <sup>104</sup>	R <sup>104</sup>	R <sup>176</sup>
	Peracetic Acid	CH <sub>3</sub> CO <sub>3</sub> H	<10%	R <sup>104</sup>	R <sup>180</sup>	Ν	C <sup>68</sup>	C <sup>68</sup>	C <sup>68</sup>	R <sup>248</sup>
			>15%	C <sup>104</sup>	Ν	Ν	C <sup>68</sup>	C <sup>68</sup>	C <sup>68</sup>	R <sup>248</sup>
	Potassium Permanganate	KMnO <sub>4</sub>	Aqueous	C <sup>104</sup>	R <sup>104</sup>	Ν	C <sup>104</sup>	R <sup>140</sup>	R <sup>140</sup>	R <sup>248</sup>
	Sulfur dioxide	SO <sub>2</sub>	Aqueous	R <sup>104</sup>	R <sup>68</sup>	-	R <sup>104</sup>	R <sup>104</sup>	R <sup>140</sup>	R <sup>68</sup>
	Sodium Hypochlorite <sup>††</sup>	NaOCI	12.5%	R <sup>104</sup>	R <sup>200</sup>	Ν	Ν	C <sup>104</sup>	R <sup>104</sup>	R <sup>140</sup>
			15%†	R <sup>68</sup>	R <sup>200</sup>	Ν	Ν	C <sup>104</sup>	R <sup>104</sup>	R <sup>140</sup>
	Sodium Sulfite	Na <sub>2</sub> SO <sub>3</sub>	Saturated	R <sup>68</sup>	R <sup>176</sup>	R <sup>140</sup>	R <sup>104</sup>	R <sup>140</sup>	R <sup>140</sup>	R <sup>248</sup>
	Sodium Bisulfite	NaHSO3	Saturated	R <sup>140</sup>	R <sup>140</sup>	R <sup>122</sup>	R <sup>104</sup>	R <sup>176</sup>	R <sup>212</sup>	R <sup>248</sup>
	Sodium Metabisulfite	Na <sub>2</sub> S <sub>2</sub> O <sub>5</sub>	Saturated	R <sup>68</sup>	-	R <sup>140</sup>	R <sup>104</sup>	R <sup>68</sup>	R <sup>68</sup>	R <sup>122</sup>
	Sodium Permanganate	NaMnO4	20%	C <sup>68</sup>	-	_	_	R <sup>68</sup>	R <sup>140</sup>	R <sup>140</sup>

RATINGS

Chemical compatibility ratings are specific to our products suppliers. The absence of any class indication for any given materials, signifies the absence of data for such material(s) with respect to the specific chemical(s), temperature(s) and concentration(s).

Note: Chemical resistance data is determined in a laboratory setting and cannot account for all possible variables of an installed application. It is up to the design engineer or final user to use this information as guidance for a specific application design. If a material is chemically resistant to the concentrated form of a specific chemical, it should be resistant to the diluted form of that same chemical. Ratings outside of the temperature and pressure range may be possible, please contact IPEX for more information.



\*\* PTFE Diaphragm valve with spigot or flanged ends are available

<sup>+</sup> IPEX's unique and specifically engineered formula

<sup>++</sup> Vented ball valve required

# SALES AND CUSTOMER SERVICE

IPEX USA LLC Toll Free: (800) 463-9572 ipexna.com

#### About the IPEX Group of Companies

As leading suppliers of thermoplastic piping systems, the IPEX Group of Companies provides our customers with some of the world's largest and most comprehensive product lines. All IPEX products are backed by more than 50 years of experience. With state-of-the-art manufacturing facilities and distribution centers across North America, we have established a reputation for product innovation, quality, end-user focus and performance.

Markets served by IPEX group products are:

- Electrical systems
- Telecommunications and utility piping systems
- Industrial process piping systems
- Municipal pressure and gravity piping systems
- Plumbing and mechanical piping systems
- Electrofusion systems for gas and water
- · Industrial, plumbing & mechanical, and electrical cements
- Irrigation systems
- PVC, CPVC, PP, PVDF, PE, and ABS pipe and fittings

Xirtec<sup>®</sup> is a registered trademark used under license. . Xirtec<sup>®</sup> CPVC piping systems are made with Corzan<sup>®</sup> CPVC compounds.

Corzan<sup>®</sup> is a registered trademark of the Lubrizol Corporation.

This literature is published in good faith and is believed to be reliable. However, it does not represent and/or warrant in any manner the information and suggestions contained in this brochure. Data presented is the result of laboratory tests and field experience.

A policy of ongoing product improvement is maintained. This may result in modifications of features and/or specifications without notice.



BRINNAIP200704U © 2020 IPEX IND0029U

